

Hello Ted,

We recently tested your two foam products to ASTM C518. The ATI job number was 96609.01-116-25. The results were as follows:

Sample A: 1 PCF Foam Reflective / Reflective= R 3.81

Sample B: 2 PCF Foam Reflective / White Laminate= R 4.18

Thanks you,

**Dale C. white**

**NFRC Certified Simulation Technician**

130 Derry Court

York, PA 17406

**Main:** 717.764.7700

**Fax:** 717.764.4129

**Email:** [dwhite@archtest.com](mailto:dwhite@archtest.com)

**Web:** [www.archtest.com](http://www.archtest.com)

**Architectural Testing**

**"The POWER in Performance Testing...**

**...the FORCE in Certification Services"**